

# DuPont™ Delrin®

acetal resin

## Delrin® 500P NC010

Delrin® 500P is a medium viscosity acetal homopolymer for injection molding. It has improved processing thermal stability, good mechanical properties, and low volatile emissions.

Property	Test Method	Units	Value
<b>Identification</b>			
Resin Identification	ISO 1043		POM
Part Marking Code	ISO 11469		>POM<
<b>Mechanical</b>			
Yield Stress	ISO 527	MPa (kpsi)	70 (10.1)
Yield Strain	ISO 527	%	17
Strain at Break	ISO 527	%	
50mm/min			40
Nominal Strain at Break	ISO 527	%	30
Tensile Modulus	ISO 527	MPa (kpsi)	3100 (450)
Tensile Creep Modulus	ISO 899	MPa (kpsi)	
1h			2800 (406)
1000h			1600 (232)
Flexural Modulus	ISO 178	MPa (kpsi)	2900 (420)
Flexural Stress	ISO 178	MPa (kpsi)	
@ 3.5% Strain			80 (11.6)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m <sup>2</sup>	
-30°C (-22°F)			8
23°C (73°F)			9
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m <sup>2</sup>	
-30°C (-22°F)			240
23°C (73°F)			300

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc  
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.  
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2010

100216/100930

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications ... H-50102-3

**Delrin® 500P NC010**

Property	Test Method	Units	Value
<b>Thermal</b>			
Deflection Temperature 0.45MPa	ISO 75-1/-2	°C (°F)	158 (316)
1.80MPa			94 (201)
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	178 (352)
CLTE, Parallel -40 - 23°C (-40 - 73°F)	ISO 11359-1/-2	E-4/C (E-4/F)	1.0 (0.56)
23 - 55°C (73 - 130°F)			1.1 (0.61)
55 - 100°C (130 - 212°F)			1.5 (0.82)
CLTE, Normal -40 - 23°C (-40 - 73°F)	ISO 11359-1/-2	E-4/C (E-4/F)	1.0 (0.56)
23 - 55°C (73 - 130°F)			1.1 (0.61)
55 - 100°C (130 - 212°F)			1.6 (0.9)
Specific Heat	ISO 11357-4	J/kg K (Btu/lb F)	3000 (0.71)
Vicat Softening Temperature 50N	ISO 306	°C (°F)	155 (310)
<b>Rheological</b>			
Melt Mass-Flow Rate 190°C, 2.16kg	ISO 1133	g/10 min	15
Melt Volume-Flow Rate	ISO 1133	cm <sup>3</sup> /10 min (ml/10 min)	13
<b>Electrical</b>			
Surface Resistivity	IEC 60093	ohm	1E15
Volume Resistivity	IEC 60093	ohm m	1E12
Relative Permittivity 1E2 Hz	IEC 60250		3.9
1E6 Hz			3.9
Dissipation Factor 1E6 Hz	IEC 60250	E-4	60
CTI	IEC 60112	V	600

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc  
ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.  
Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2010

100216/100930

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications ... H-50102-3

## Delrin® 500P NC010

Property	Test Method	Units	Value
<b>Flammability</b>			
Flammability Classification 0.75mm	IEC 60695-11-10		HB
Flammability Classification 0.75mm	UL94		HB
Oxygen Index	ISO 4589-1/-2	%	22
High Amperage Arc Ignition Resistance 0.75mm	UL 746A	arcs	200
Hot Wire Ignition 0.75mm	UL 746A	s	8
			11
			15
<b>Temperature Index</b>			
RTI, Electrical 0.75mm	UL 746B	°C	50
			110
			110
RTI, Impact 0.75mm	UL 746B	°C	50
			85
			90
RTI, Strength 0.75mm	UL 746B	°C	50
			90
			95

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc  
ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.  
Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2010

100216/100930

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications ... H-50102-3

## Delrin® 500P NC010

Property	Test Method	Units	Value
<b>Other</b>			
Density	ISO 1183	kg/m <sup>3</sup> (g/cm <sup>3</sup> )	1420 (1.42)
Hardness, Rockwell	ISO 2039/2		
Scale M			92
Scale R			120
Water Absorption	ISO 62, Similar to	%	
Equilibrium 50%RH			0.3
Immersion 24h			0.6
Saturation, immersed			1.4
Molding Shrinkage	ISO 294-4	%	
Normal, 2.0mm			1.9
Parallel, 2.0mm			2.0
<b>Processing - Injection Molding</b>			
Melt Temperature Range		°C (°F)	210-220 (410-430)
Melt Temperature Optimum		°C (°F)	215 (420)
Mold Temperature Range		°C (°F)	80-100 (175-210)
Mold Temperature Optimum		°C (°F)	90 (195)
Drying Time, Dehumidified Dryer		h	2-4
Drying Temperature		°C (°F)	80 (175)
Processing Moisture Content		%	<0.2
Hold Pressure Range		MPa (kpsi)	80-100 (12-15)

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc  
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.  
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Delrin® are trademarks or registered trademarks of DuPont Company. Copyright© 2010

100216/100930

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-3 and DuPont CAUTION Regarding Medical Applications ... H-50102-3